

Swell-able Water-bar for In-situ Concrete

DESCRIPTION

TIKISWELL is tough and flexible active joint sealing swell-able profile used to prevent the passage of water through non-movement joints in both new in-situ concrete and between new and existing concrete.

TIKISWELL consist of high performance hydrophilic swell-able acrylic composition and thermoplastic elastomer.

TIKISWELL when comes in contact with water, increases in volume up to a maximum of 300% and imparts resistance to hydraulic pressure.

Swelling of **TIKISWELL** in fresh concrete is minimal thereby maximizing the positive pressure seal provided by the hydrophilic bar to the protected joint.

The advanced hydrophilic groups in **TIKISWELL** are not subject to extraction nor to the loss of swelling performance by prolonged or repeated wetting and drying cycle.

The unique swelling action of **TIKISWELL** creates a positive pressure against the face of the concrete joint, thus preventing water passage through the protected joint.

USES

TIKISWELL is used to:

- Waterproof casting and header joints in concrete.
- Waterproof joints between pre-cast concrete elements.
- Waterproof around all sorts of transitions and penetrations in in-situ concrete.
- Waterproof stationary joints.
- Waterproof connecting joints.

ADVANTAGES

- Easy to install
- Swelling properties unaffected by long term wetting or drying cycles.
- Delayed swell action allows extra tolerance on site during fresh concrete pour.
- Sustains effective seal in wet conditions
- Retains its shape without splitting or cracking, even at maximum swelling.
- Elastomeric properties are retained in maximum swelling state.
- Bentonite free.

PROPERTIES

Form	Rectangular section elastomeric strips.
Standard dimension TIKISWELL 2010 TIKISWELL 2005 TIKISWELL 1010	20mm x 10mm x 10 mtr. 20mm x 05mm x 20 mtr. 10mm x 10mm x 20 mtr.
Solid content	100%
Unrestrained volumetric expansion	Up to 300%
Application temperature	-20°C to 50°C Service
Service temperature range	-30°C to 70°C
Hydrostatic pressure resistance	Up to 60 meters (6 bars)

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surface shall be clean and dry during installation of **TIKISWELL**. A smooth surface is preferable.

APPLICATION

TIKISWELL shall be applied to the middle of the construction joint. It is advisable to allow at least 8cm of concrete on both sides of the expanding sealant to prevent cracks in the concrete.

TIKISWELL can be fixed on the substrate by using adhesive and / or by nails every 20 to 25cm.

The ends of the **TIKISWELL** bars should be placed head-to-head against each other or an overlap of 10cm at end laps.

Do not use in expansion joints.

SUPPLY

TIKISWELL is supplied in rectangular section strips. With shelf life of 2 years if placed in original packing, dry and frost free conditions.

Product	Dimension (W x H)	Packing
TIKISWELL 1010	10mm x 10mm	20 mtr. Roll
TIKISWELL 2005	20mm x 05mm	20 mtr. Roll
TIKISWELL 2010	20mm x 10mm	10mtr. Roll

STORAGE

TIKISWELL must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight.

VERSION: R1 201901

Disclaimer: TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
 Maharashtra, India. T: +91 22 4126 6699
 E: info@tikidan.in | W: www.tikidan.in

