

DANOFELT PY I-300/I-500/I-900



Non-Woven Polyester Geo-Textile

DESCRIPTION

DANOFELT PY I-300/I-500/I-900 is non-woven mechanically bonded needle punched geo-textile of 300gsm, 500gsm and 900gsm, manufactured from high quality U.V stabilized polyester short fiber.

The advanced manufacturing process produces strong, flexible and dimensionally stable geo-textile fabric structure, with optimum pore sizes and high permeability.

It is resistant to chemicals and biological degradation normally found in soils and is stabilized against degradation due to shorter exposure to ultraviolet radiation.

USES

- It is used as separating layer between two incompatible materials, avoiding their contact ensuring the maintenance of their initial performance.
- It is used as protection layer on waterproofing layer preventing the perforation and abrasion during subsequent works.
- It is used as separation, filtration, drainage, reinforcement, protection layer improving the mechanical and hydraulic behaviour in various civil engineering applications.

ADVANTAGES

- Prevents attack of or adhesions between two different in-compatible materials.
- High resistance to puncture, chemical and biological elements existing in the soil.
- Easy to install and adaptable to complex geometrics.

SUPPLY

DANOFELT PY I-300/I-500/I-900 is supplied in roll size of 5.8m x 100m (w x l).

STORAGE

DANOFELT PY I-300/I-500/I-900 must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, and direct sunlight.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOFELT PY I-300/I-500/I-900**.

PROPERTIES

Properties	Standard	Unit	DANOFELT PY I-300	DANOFELT PY I-500	DANOFELT PY I-900
Mechanical properties					
Tensile Strength	ASTM D 4595	KN/m	11	20	25
Elongation	ASTM D 4595	%	> 50	>50	>50
Grab Tensile Strength	ASTM D 4632	N	650	850	1400
Grab Tensile Elongation	ASTM D 4632	%	> 55	>55	>55
Trapezoidal Tear Strength	ASTM D 4533	N	300	500	900
Puncture Strength (CBR)	ASTM D 6241	N	1800	2400	3800
Physical properties					
Mass/Unit Area	ASTM D 5261	Gsm	300	500	900
Thickness	ASTM D 5199	mm	2.3	3.0	5.5
Hydraulic properties					
AOS	ASTM D 4751	microns	40	40	40
UV Resistance @ 150 hrs.	ASTM D 4355	% Strength Retained	>85	>85	>85

Disclaimer: TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
Maharashtra, India. T: +91 22 4126 6699

E: info@tikidan.in | W: www.tikidan.in

