

Acrylic Polymer Modifier for Cementitious Systems

DESCRIPTION

TIKI POLYMOD AR-HS is acrylic polymer based polymer modifier for use with cementitious compositions as waterproofing slurry coating, water resistant bonding agent, protective coating.

USES

As polymer modifier in conjunction with cementitious composition, **TIKI POLYMOD AR-HS** is used for:

- Waterproofing basement and retaining wall, lift pits, toilets and bathrooms, wet areas, water tanks, swimming pools, terraces, and other areas demanding watertight treatment.
- Bonding new cementitious surfaces with old cementitious surfaces in repair works.
- Preparations of polymer modified cementitious protective coating.

ADVANTAGES

Cementitious compositions made with **TIKI POLYMOD AR-HS** is characterised by:

- Increased resistance to water ingress and cracking.
- Enhanced adhesion with substrates.
- Increased water tightness.
- Good flexibility and crack bridging ability.
- Breathable – allows entrapped moisture to escape.
- High resistance to corrosive atmosphere.
- Improved workability.
- Lower water-cement ratio.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surface to be treated must be clean and sound free of loose dust, laitance, foreign particles, curing compound, mould release agent & other contaminants that may compromise adhesion of treatment adversely.

Spalled concrete or honeycombed surface should be repaired using polymer modified cementitious repair mortar modified with **TIKI POLYMOD SBR**.

Cracks should be cut to V-shape and filled using cementitious mortar modified with **TIKI POLYMOD SBR**.

Never use **TIKI POLYMOD AR-HS** modified waterproofing slurry directly on unsound surface, brick coba or lime mortar.

PROPERTIES of TIKI POLYMOD AR-HS

Properties	Values
Appearance	Milky white pourable emulsion
Emulsifying System	Synthetic anionic
Total Solids (%)	57 ± 1.0
pH at 25°C	8.0 ± 0.5
Brookfield Viscosity RVT (CPS) SP.3, 20 RPM at 25°C	2500 Max.
Density (gm/cm ³)	1.015 ± 0.015
Compatibility	Compatible with all grades of cement

POLYMER MODIFIED CEMENTITIOUS WATERPROOFING MIX PREPARATION

2 parts of Cement by weight is gradually added to 1 part of **TIKI POLYMOD AR-HS** by weight in a separate container under continuous stirring until homogeneous lump free creamy consistency mix is obtained. Allow the prepared mix to stand for 5 minutes before using. The prepared mix should be used within 30 minutes after mixing.

APPLICATION

Prior to application of waterproofing slurry, damp the surface to be coated by sprinkling water. Apply slurry uniformly by brush in two coats, the second coat shall be applied perpendicularly on dried first coat within 24 hours of application of first coat.

If application of protective render coat is required, then quartz sand is sprinkled on the wet second coat for forming mechanical key for subsequent protection coat.

COVERAGE

Waterproofing slurry coat consisting of mixture of 1 Kg. of **TIKI POLYMOD AR-HS** with 2 Kg. of cement covers 1.4 to 1.6 m² area @ 1mm thickness in 2 coats.

PROPERTIES of WATERPROOFING SLURRY

Properties*	Values
Mix Ratio Cement : TIKI POLYMOD AR-HS	2:1 by Weight
Mix Density	1800 to 2000 Kg./m ³
Pot Life	40 minutes @ 30°C 20 minutes @ 40°C
Re-Coatability	6 to 24 hours

*Properties are indicative, tested under ideal laboratory condition. Properties Varies depending on site conditions and mix constituents.

BOND COAT

TIKI POLYMOD AR-HS with minimum solid content of ≥55% by weight can be suitably used as bonding slurry coat to promote the adhesion of cementitious treatments with cementitious substrate. **TIKI POLYMOD AR-HS** should be mixed with cement in 1:1 ratio by weight and applied @ 4 to 6 m²/ Kg., as bond coat, to produce minimum pull-off bond strength of >1MPa.

Disclaimer: **TIKI TAR DANOSA** warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While **TIKI TAR DANOSA** endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by **TIKIDAN** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **TIKIDAN**, are responsible for carrying out procedures appropriate to a specific application. **TIKIDAN** reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

VERSION: R1, 201904

CURING

The final layer of applied polymer modified cementitious systems shall be allowed to initially cure for at least 3 days by spraying water and thereafter shall be allowed to dry out for air curing.

SUPPLY

TIKI POLYMOD AR-HS is supplied in 5Kg., 20Kg. and 210Kg. pack sizes.

STORAGE

TIKI POLYMOD AR-HS must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight. The shelf life is 12 months in sealed unopened container.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **TIKI POLYMOD AR-HS**. Use gloves, goggles and barrier cream. Avoid contact with skin. Ensure adequate ventilation during application. For further detail, refer to Material Safety Data Sheet.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078, Maharashtra, India. T: +91 22 4126 6699
E: info@tikidan.in | W: www.tikidan.in

